

TECHNICAL DATA SHEET

Office Premium Cut-Size

Physical Parameters

| | REFERENCE | TARGET | TYPICA | VALUES |
|----------------------------|-----------------|--------|--------|--------|
| Basis Weight, g/m² | ISO 536 | 75.0 | 72.0 | 78.0 |
| Thickness, μm | ISO 534 | 105 | 101 | 109 |
| Stiffness MD, mN | ISO 2493-1 | | ≥ 90 | |
| Stiffness CD, mN | ISO 2493-1 | | ≥ 35 | |
| Tensile MD, kN/m | ISO 1924-2 | | ≥ 4.5 | |
| Bendtsen Roughness, ml/min | ISO 8791-2 | 180 | 140 | 220 |
| Air Permeability, ml/min | ISO 5636-3 | | | ≤ 1700 |
| Moisture, % | ISO 287 | 4.0 | 3.5 | 4.5 |
| Formation, # | Internal Method | | ≥ 25 | |

Optical Parameters

| | REFERENCE | TARGET | TYPICAL | VALUES |
|-------------------|------------|--------|---------|--------|
| Whiteness, CIE | ISO 11475 | 169 | 166 | 172 |
| Brightness D65, % | ISO 2470-2 | 112 | 109 | 115 |
| Opacity, % | ISO 2471 | 93 | ≥ 91 | |

Approved by:

Product Development and Technical Services: Eng. Vitor Crespo

